



March 2010

## Earthwool® DriTherm Cavity Slabs

### For masonry cavity walls

#### Description

Earthwool DriTherm Cavity Slabs are semi-rigid or rigid slabs of non-combustible, water repellent, glass mineral wool. They are 455mm wide to suit standard vertical wall tie spacings, ensuring a closed joint with adjacent slabs.

#### Application

Earthwool DriTherm Cavity Slabs are for the thermal insulation of masonry cavity external walls, either partially filling or fully filling the cavity. They are approved for use in buildings up to 12m high in any exposure zone and for use in multi-storey applications up to 25m in height.

#### Standards

Earthwool DriTherm Cavity Slabs are non-combustible glass mineral wool, defined as mineral wool in BS 3533: 1981 and are manufactured in accordance with BSI Quality Assurance Standard BS EN ISO 9001: 2000, and Product Standard EN 13162.

#### Guarantee

Earthwool DriTherm Cavity Slabs are guaranteed\* for 50 years to resist the transmission of liquid water from the outer masonry leaf to the inner masonry leaf in new external cavity walls and to have a thermal conductivity of 0.032 to 0.037 W/mK at normal building temperatures.

#### Durability

Earthwool DriTherm Cavity Slabs are odourless, rot proof, non-hygroscopic, do not sustain vermin and will not encourage the growth of fungi, mould or bacteria.

### Performance

#### Thermal

Earthwool DriTherm Cavity Slabs have thermal conductivities ranging from 0.032 to 0.037 W/mK.

#### Fire

Earthwool DriTherm Cavity Slabs are classified as Euroclass A1 to BS EN ISO 13501-1.

### Benefits

- British Board of Agrément approved for use in all exposure zones
- Excellent thermal and fire performance
- Water repellent
- Slabs 'knit' together, thus eliminating air gaps between adjacent slabs

\* Available by application to Knauf Insulation.

## Earthwool® DriTherm Cavity Slabs

### Certification

Earthwool DriTherm Cavity Slabs are certified by British Board of Agrément Certificate 95/3212. Approval can be sought from Knauf Insulation Ltd and the British Board of Agrément for Earthwool DriTherm Cavity Slab's use in buildings over 25m high.

### Environmental

Earthwool DriTherm Cavity Slabs are free from CFCs, HCFCs and any other material with ozone depletion potential in their manufacture and content and represent no known threat to the environment. **Earthwool DriTherm Cavity Slab's manufacture has a low impact on the environment and is classified as Zero ODP and Zero GWP.**

### Vapour resistance - resistivity

Earthwool DriTherm Cavity Slabs offer negligible resistance to the passage of water vapour and have a vapour resistivity of 7.00MN/g.m.

### Moisture resistance

Tests by the British Board of Agrément confirm that Earthwool DriTherm Cavity Slabs will not transmit water to the inner leaf. Nor will they transmit moisture by capillary action across the cavity or from below DPC level.

### Handling and storage

Earthwool DriTherm Cavity Slabs are easy to handle and install, being lightweight and easily cut to size, where necessary. They are supplied in polythene packs which are designed for short term protection only. For longer term protection on site, the product should either be stored indoors, or under cover and off the ground. Installation instructions are on every pack. Earthwool DriTherm Cavity Slabs should not be left permanently exposed to the elements.

Thickness (mm)	Thermal conductivity (W/mK)	Thermal resistance (m <sup>2</sup> K/W)	Length (m)	Width (mm)	Slabs per pack	Area per pack (m <sup>2</sup> )
<b>Earthwool DriTherm 37 Standard</b>						
125	0.037	3.35	1200	455	10	5.46
100	0.037	2.70	1200	455	12	6.55
85	0.037	2.25	1200	455	16	8.74
75	0.037	2.00	1200	455	16	8.74
65	0.037	1.75	1200	455	16	8.74
50	0.035	1.40	1200	455	16	8.74
<b>Earthwool DriTherm 34 Super</b>						
100	0.034	2.90	1200	455	8	4.37
85	0.034	2.50	1200	455	8	4.37
75	0.034	2.20	1200	455	10	5.46
65	0.034	1.90	1200	455	12	6.55
<b>Earthwool DriTherm 32 Ultimate</b>						
100	0.032	3.10	1200	455	6	3.28
85	0.032	2.65	1200	455	8	4.37
75	0.032	2.30	1200	455	8	4.37
65	0.032	2.00	1200	455	10	5.46

All dimensions are nominal

Ref: ED131710

Knauf Insulation mineral wool products with ECOSE® Technology benefit from a formaldehyde-free binder made from rapidly renewable bio-based materials instead of petroleum-based chemicals which is up to 70% less energy intensive. The technology has been developed for Knauf Insulation's glass and rock mineral wool products, enhancing their environmental credentials without affecting the thermal, acoustic or fire performance. Insulation products made with ECOSE® Technology contain no dye or artificial colours – the colour is completely natural.

### Knauf Insulation Ltd

PO Box 10  
Stafford Road  
St Helens  
Merseyside  
WA10 3NS

### Customer Service (sales)

Tel: 0844 800 0135

### Technical Advisory Centre

Tel: 01744 766 666

### Literature

Tel: 08700 668 660

[www.knaufinsulation.co.uk](http://www.knaufinsulation.co.uk)

For more information please visit  
[www.knaufinsulation.co.uk](http://www.knaufinsulation.co.uk)